



Solid Round Wire

Soft or Annealed Copper Wire

ROD Type	ETP Rod in accordance with the C11040 Standard Code
Standard	ASTMB 3 - 13
Diameter (mm)	0.6 - 3.6 $\pm$ 1%
Elongation (Primary Length 250 mm)%	in accordance with the Table 1 ASTMB3 - 13 Standard code
Resistivity (20 °C)	< 0.15328 Ω .g /m ² or < 0.17241 Ω .mm ² /m
Packaging	On Wooden or Metal Reel, Octabin